

EXTERIOR WALLS – MEMBRANE SYSTEM

APPLICATION GUIDE

- PREPARATION:** See table below for the preparation process for various substrates.
- CLEAN:** The surface must be cleaned using a high-pressure cleaner. If surface has been previously painted, ensure compatibility with existing coating and removal of any previous coating that is blistered, loose, or flaking. Ensure flaking paint is removed to provide a sound, clean surface.
- To avoid damage, due care should be taken on previously painted surfaces when using a pressure cleaner.
- STERILISE:** Prior to coating the surface, *Prepcote Surface Treatment* is applied to sterilise fungal and algae growth. Inadequate application will void any warranty.
- Spray *Prepcote* to any fungi/mould affected areas with an atomising gun. Allow 4 hours prior to coating with the *Primecote Sealer Primer*. Please note that *Prepcote Surface Treatment* is not a cleaning product, it is to remain on the surface to form part of the Globalcote system.
- SURFACE SEALED:** To ensure maximum adhesion the entire roof area needs to be thoroughly coated with *Primecote Façade* at a spread rate of 6-8m² per litre.
- Once suitably primed there should be a visible shine evident on the surface.
- 1st COAT:** First coat of *Globalcote Membrane* is applied at a spread rate of 5m² per litre.
- 2nd COAT:** Second coat of *Globalcote Membrane* is applied at a spread rate of 5m² per litre.

It is recommended that the application process is carried out by a skilled applicator who is fully conversant with the Globalcote Products and systems, to validate the material warranty conditions. It is also the responsibility of the Applicator to ensure that the substrate is of an acceptable standard prior to the application of the Globalcote Coating System. The Globalcote Membrane Coating will only follow the contour of the substrate, therefore in certain light conditions imperfections may be evident. This issue is not product related.

NOTE:

1. The surface preparation is the responsibility of the Builder, Renovator, Contractor or Applicator.
2. Do not apply where rain is imminent. High humidity and/or low temperatures may effect curing times. Weather conditions must be considered and deemed suitable before proceeding with application of the Globalcote system.

SURFACE OR SUBSTRATE	PREPARATION PROCESS
<p>Rejuvenate Existing Rendered, Textured or previously painted Masonry Surfaces - UNIVERSAL EXTERIOR</p>	<p>Ensure Globalcote compatibility with existing coating. Ensure removal of any previous coating that is blistered, loose, or flaking using a high-pressure cleaner. Ensure surface is dry prior to coating. Ensure surface is not subject to hydrostatic pressure. If mould or mildew is evident, pre-treat the surface with <i>Prepcote Surface Treatment</i> and allow to dry prior to coating. Repair and/or replace render or texture where required and allow to cure or dry.</p>
<p>New & Uncoated Pre-blended Render - EXTERIOR New & Uncoated Conventional Sand & Cement Render - EXTERIOR</p>	<p>Ensure Pre-Blended Rendered surface has 7 days curing prior to coating. Ensure Conventional Sand and Cement Render has 28 days curing prior to coating. Ensure moisture content is less than 6% at time of application to allow optimum coating performance. Ensure surface is not subject to hydrostatic pressure. Ensure surface is clean, dry and dust free.</p>
<p>New & Uncoated Off Form Concrete - EXTERIOR New & Uncoated Tilt-Up and Pre-Cast Panels – EXTERIOR New & Uncoated Brick and Concrete Block - EXTERIOR</p>	<p>Ensure all cementitious surfaces are fully cured prior to coating. Ensure moisture content is less than 6% at time of application to allow optimum coating performance. Ensure surface is not subject to hydrostatic pressure. Ensure all foreign material and contaminants (including Bond Breakers & release agents) that may affect the adhesion of the Globalcote Membrane System are removed prior to coating. Ensure surface is free from mould or mildew. Pressure wash and treat with <i>Prepcote Surface Treatment</i> prior to coating.</p>
<p>New and Uncoated Fibre Cement Sheets - EXTERIOR</p>	<p>Ensure Fibre Cement sheets are securely fixed in accordance with manufacturer's specifications. Ensure that there is no possibility of future sheet movement. Ensure surface is not subject to hydrostatic pressure. Ensure surface is clean, dry and dust free.</p>

HEALTH & SAFETY

- **Contact Poisons Information Centre (Phone Australia: 13 11 26) or a doctor.**
- **IF SWALLOWED:** Rinse mouth. Do NOT induce vomiting.
- **IF ON SKIN:** Wash with plenty of soap and water.
- **IF INHALED:** Remove victim to fresh air and keep at rest in a position comfortable for breathing.
- **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- **IF EXPOSED OR CONCERNED:** Get medical advice/attention.
- Wear appropriate protective clothing, gloves, eye/ face protection and suitable respirator.

RECOMMENDATIONS & PRECAUTIONS

- Use this product in a well-ventilated area.
- Ensure that the application of the product is in accordance with Globalcote recommendations.
- Due care and consideration should be taken where water collection methods are present. Globalcote recommends allowing 10 days curing and an initial rinse (rain or tap water wash) prior to reconnecting water collection systems.
- The surface preparation is the responsibility of the Builder, Renovator, Contractor or Applicator. It is also the responsibility of the Applicator to ensure that the substrate is of an acceptable standard prior to the application of the Globalcote Coating System.

DISCLAIMER: The recommendations and data provided in this document are true and accurate at the time of testing. The information is given in good faith but without any guarantee as conditions and methods of use on the Globalcote product are beyond Globalcote's control. Globalcote recommends that the applicator of this product conducts a small test patch in an inconspicuous area to determine the suitability of the Globalcote material and its recommendations prior to use or application.